



# The LHC Collimation project



## *LHC Collimators for Phase 1*

**Effects of the 450GeV accident case (TT40 experiment) on the jaw metal support (preliminary report)**

***71st Collimator design meeting 01/09/2005***

***Alessandro Bertarelli***

***Alessandro Dallocchio***





# Thermo-mechanical Analysis



## Outline

- **TT40 test results**
- **Preliminary interpretation**
- **Simplified “didactic” model**
- **Actual model**
- **Outlook and conclusions**



# Thermo-mechanical Analysis



Controls on prototype #2 after TT40 test (5  $3.2 \times 10^{13}$  p shots plus many more at lower intensity) ...

- No sign of mechanical damage on both C/C and graphite jaw (in agreement with calculations).
- No permanent deformation of jaws.
- Permanent bending of metal support ( $\sim 300 \div 350 \mu\text{m}$ )


**No in-depth calculations were done so far on the metal support for the accident cases (all focus on the jaws) ... this has to be reconsidered!!**



# Thermo-mechanical Analysis



Temperature profile after  $7.2 \mu\text{s}$  (5 mm offset)  
"hottest" cross-section





# Thermo-mechanical Analysis



## A simplified theory to justify permanent bending deformation ... (1)

- The metal support is free to expand, but because of the rapidity of the thermal shock it acts “as if” no expansion is allowed  $\Rightarrow$  **compression stresses** arise ...
- For copper a  $\Delta T = 70^\circ\text{C}$  with prevented expansion leads to  $\sigma_z = -E\alpha\Delta T \cong -140\text{MPa}$ . This is well above yield strength of OFE-Cu ( $\sim 50\text{MPa}$ )  $\Rightarrow$  Plastic compressive deformation of 3mm Cu plate (and partially Cu pipes) ( $\varepsilon_z < 0$ )  $\Rightarrow$  Bending of the support **away from the beam!**



# Thermo-mechanical Analysis



## A simplified theory to justify permanent bending deformation ... (2)

- Vibrations are induced. Can successive tensile stresses lead to a “counter-plasticization” and positive permanent strains?
- An in-depth **coupled thermo-mechanical transient elasto-plastic** analysis is necessary!!
- Unfortunately such a non-linear analysis is very time-consuming
  - shot duration  $7 \mu\text{s} \Rightarrow$  calculation time-step  $\leq 1 \mu\text{s}$
  - Flexural eigen-frequencies  $\Rightarrow > 15 \text{ ms}$
  - At least several periods must be studied  $\Rightarrow$  time-span  $> 0.1 \text{ s}$
  - Number of calculation substeps  $> 150000 \Rightarrow$  CPU time  $\sim 15 \text{ s/substep} \Rightarrow$   
 **$> 25 \text{ days of calculation for a full model}$**



# Thermo-mechanical Analysis




A simplified model is first used to understand the “basics” of the phenomenon and get results in a short time ...

15 mm thick, 1 m long beam, bi-metal

3 mm elasto-plastic Cu ( $\sigma_0 = 50$  MPa)

12 mm fully elastic Glidcop ( $\sigma_0 = 300$  MPa)



Temperature increasing from 27°C to 97° in 7  $\mu$ s on all Cu strip


Heat diffusion taken into account  
Density artificially reduced to “accelerate” the process  
 $\nu=0$  to avoid mechanical coupling



# Thermo-mechanical Analysis



## Results for the simplified didactic model








# Thermo-mechanical Analysis



## Results for the simplified didactic model (2)



This is due to the fact that the permanent deformations on the Cu plate remain always negative

Longitudinal plastic strain on Cu-plate at mid span




# Thermo-mechanical Analysis



## Results for the simplified didactic model (3)

### What happens if a fully elastic model is used?



Bending stress at mid-span on Cu-strip face

Compressive stress on Cu-plate would reach 200MPa, because of dynamic effect



# Thermo-mechanical Analysis




## 3-D full model of metal support

TT40 prototype simulation  
(i.e. Cu-OFE for pipes and  
plate, Steel for C-bar)

Actual energy distribution  
from FLUKA runs (linearly  
increasing during  $7.2\mu\text{s}$ )

Elasto-plastic behavior for  
all materials




---  
PLOT




# Thermo-mechanical Analysis



## Results for the 3-D full model (analysis stopped at 13ms)



The displacement pattern seems to be the same as for simplified model, with a z non-uniformity





Transverse displacement at circa mid-span



# Thermo-mechanical Analysis



## Results for the 3-D full model (analysis stopped at 13ms)



Longitudinal strains are always negative and seem to have stabilized after some millisecond.


$\epsilon_z$  at 900 mm



# Thermo-mechanical Analysis



## Results for the 3-D full model (analysis stopped at 13ms)



A certain degree of plasticization is found also on pipes (here in Cu-OFE)



# Thermo-mechanical Analysis



## Conclusions and outlook

- A preliminary “quasi-static” theory predicts that a permanent bending away from the beam is justified
- A simplified numerical model confirms this theory
- Partial results for the 3D full model are in agreement with simplified model. One might reasonably predict that permanent deformations compatible with those measured might be expected.
- Given the level of elastic stress, the substitution of OFE-Cu with Glidcop for the Cu-plate seems the best solution.
- A limited degree of plasticization might be expected on the pipes even if in CuNi
- A new full analysis with definitive materials is mandatory.